



Saremco print CROWNTEC

Technical Data

Consistency	middle viscos homogeneous liquid
Colour	According to Vita Shades (A2, A3, A3.5, A4, B2, B3, C3, C4, D3)
Depth of cure (DIN EN ISO 4049)	$\geq 1,5$ mm
Flexural strength (DIN EN ISO 4049)	> 130 MPa
E-Modulus (DIN EN ISO 4049)	> 4000 MPa
Barcol-Hardness	> 40
Shelf-life	2 years